

namal

7043.01 - 7043.42



binder

upholstery 02

description

crêpe upholstery fabric

composition

100% flame retardant polyester

width

± 150 cm, ± 59 inches

weight

± 540 gr/m¹, ± 17 oz/yd¹ fabrics

flame retardancy

EN 1021/1-2

BS 5852, crib 5

NF P 92/503-507, M1

DIN 4102, B1

UNI 9175, classe 1

Cal TB 117-2013

NFPA 260, class 1

abrasion

ISO 12947-2

25.000 rubs martindale

ASTM D4157

100.000 double rubs wyzenbeek

pilling

ISO 12945-2

4 (scale 1– 5)

ASTM D3511

5 (scale 1– 5)

colorfastness to crocking

ISO 105-X12

wet 4-5 / dry 4-5 (scale 1– 5)

AATCC 8

wet 5 / dry 5 (scale 1– 5)

colorfastness to light

ISO 105-B02

4 - 5 (scale 1 – 8)

AATCC 16.3: 40 hours

4 (scale 1– 5)

seam slippage

ISO 13936 - 2

warp 2 mm / weft 2.8 mm

ASTM D4034

warp 52 lbs / weft 51 lbs

breaking strength

ASTM D5034

warp 311 lbs / weft 213 lbs

flexibility

ISO 13937-3

A

care




namal


7043.01 - 7043.42




7043.02



7043.01




7043.17




7043.20




7043.18




7043.27



7043.23



7043.19



7043.24




7043.05




7043.04




7043.03




7043.25



7043.21




7043.26




7043.36



7043.34



7043.35



7043.08




7043.07



7043.06




7043.28




7043.22




7043.38



7043.37



7043.39



7043.40



7043.11



7043.13




7043.09



7043.10



7043.29




7043.30



7043.33



7043.42



7043.41



7043.12



7043.15



7043.16



7043.14



7043.31



7043.32